



5406M

September 2011

PRODUCT DESCRIPTION

5406M provides the following product characteristics:

Technology	Oxime Silicone
Appearance	White liquid
Product Benefits	<ul style="list-style-type: none"> • One component, requires no mixing • High thermal conductivity • Flexible • Non-Corrosive • Good adhesion • Fast surface cure
Cure	Room temperature vulcanizing (RTV)
Application	Thermal adhesive
Typical Applications	Thermal interface adhesive, Thermal sensor potting

5406M flexible, RTV silicone adhesive is engineered to enhance load bearing and shock absorbing properties of the bonded area. This material is also used to protect electrical devices from corrosion and mechanical stress such as vibration.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - CP51, 25 °C, :	
Speed 1 rpm	150,000
Extrusion Rate, g/min:	
Pressure 0.6 MPa, temperature 25 °C:	
Semco Cartridge	400 to 900
Specific Gravity @ 25°C	2.5
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

Recommended Curing Conditions

7 days @ 23 °C , 50% relative humidity

Tack Free Time

Tack Free Time, @ 22°C/50% RH, minutes 3 to 10

5406M quickly forms a skin of cured material, then slowly cures to a solid elastomer in 1 to 2 days. The curing rate and depth of cure is greatly influenced by environmental temperature and humidity.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 1 week @ 23 °C / 50±5% RH

Physical Properties:

Coefficient of Thermal Conductivity, ASTM D5470-95, 1.5 W/mK	
Coefficient of Thermal Expansion , TMA, ppm/°C	<145
Hardness, , Durometer A, ATSM D2240	70
Tension Strength, ASTM D412:	
N/mm ²	2.5
(psi)	362
Elongation , ASTM D412,%	102

TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 week @ 23 °C / 50±5 % RH

Lap Shear Strength, ISO 4587:

Steel to Steel :

0 gap	N/mm ²	2.1
	(psi)	(304)

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

DIRECTIONS FOR USE

1. This product is sensitive to moisture. Exposing adhesive directly to air will cause the adhesive to cure.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 to 28 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference 0.0